

EFALON® GLASS FABRIC TECHNICAL VALUES

| Definition* | Nominal Thickness (mm) | Nominal Weight** (gr/cm ²) | Ptfe Ratio % | Tension Resistance (N/5 cm) |
|--|------------------------|--|--------------|-----------------------------|
| Efalon® Glass Fabric | | | | |
| Standard | 0.08 | 155 | 68 | 800 |
| Standard | 0.13 | 270 | 60 | 1200 |
| Standard | 0.15 | 320 | 67 | 1200 |
| Standard | 0.25 | 530 | 62 | 2300 |
| Standard | 0.32 | 620 | 54 | 3300 |
| Standard | 0.75 | 650 | 39 | 3800 |
| Efalon® Adhesive Glass Fabric *** | | | | |
| Adhesive | 0.08 | 140 | 65 | 800 |
| Adhesive | 0.13 | 255 | 58 | 1200 |
| Adhesive | 0.15 | 296 | 63 | 1200 |
| Adhesive | 0.25 | 455 | 55 | 2300 |
| Efalon® Antistatic Glass Fabric | | | | |
| Antistatic | 0.13 | 255 | 58 | 1200 |
| Antistatic | 0.25 | 480 | 58 | 2300 |
| Antistatic | 0.35 | 710 | 59 | 3300 |

EFALON® is a registered trademark of Polikim.

* Standard width 1000mm. Please request a quote for special dimensions.

** Weight tolerance is $gr/m^2 = \pm \%5$.

*** Does not include adhesive weight. **Efalon® Glass fabric** weight only.